

VINILMUD P30[®]

VINILMUD P30[®] is a vinylic synthetic totally water-soluble polymer and it is mainly used for the preparation of stabilizing and lubricating muds in drilling and civil engineering application. The VINILMUD P30[®] drilling fluid is easy to prepare and easy to dispose after usage. Its main characteristics are its stabilizing and lubricating properties and the possibility to be recycled many times. The rheological and stabilizing properties of the drilling fluids prepared with VINILMUD P30 are easily to detect during the usage and through easy tests which can also be performed directly on job site.

Appearance	Opaque to White free flowing granular solids
Specific Gravity:	1.00-1.01 (Water = 1.00)
Density	0,6 – 0,7 g/cm ³
Marsh Viscosity:	65 – 70 sec (0,1% in tap water, salt water and hard water)
Filtration properties	medium – low

PREPARATION

In order to prepare VINILMUD P30[®] based fluids, it is not necessary to have special equipments such as it is needed for the preparation of bentonite based fluids. The complete hydration of the polymer is realized in approximately half an hour. The long chain of vinyl polymers such as VINILMUD P30 case, requires to the operators a strict care on the agitation speed and in particular on the kind of pump to be used for the mud injection.

A volumetric pump is preferable to a centrifuge.

DOSAGE

The VINILMUD P30[®] dosage generally varies according to the lubricating and stabilizing characteristics needed by the operators, but above all varies according to the soil condition on which the job is performed.

The dosage of polymer suitable for low permeability and clayey soils is around 0,5 Kg of product for one cubic meter of fresh water up to a dosage of 2 Kg/m³ for jobs on high permeability soils.

While using the fluid, it is extremely important to keep the pH level not lower than 10 because in this way there might be a risk of losing all stabilizing and lubricating characteristics of the fluid itself.

The way to keep the pH level over the above said value, is to add sodium hydroxide in a quantity of around 20% on polymer weight.

DISPOSAL

After usage VINILMUD P30[®] muds, before disposal, can be treated with oxidizing agents in order to be sure that any trace of active material has been eliminated.

The most popular products used for treatment of the vinyl polymer muds, are sodium hypochlorite (bleaching agent) and oxygen peroxide

Information given in this bulletin is based on the state of our knowledge at the date of publication and are believed to be accurate, but do not constitute any engagement or warranty from our part. Buyers and users should make their own assessments under their own conditions and for their own requirements. Information may be changed without any notice. For mandatory characteristics and performance please refer to our Sale Specifications.