

BENTOSUND API

BENTOSUND API is a specifically tailored bentonite specially set up for the application in oil-well drillings. Its characteristics corresponds to the **API Specification 13A**

Application

BENTOSUND API is specifically set-up for Oil/well drilling. It is suitable for all kind of soils

Preparation

Mix with water using a high efficient mixer. To get best properties 24 hours of aging is required.

Keep the mud in circulation during use.

Packaging

Jumbo bags & 25 Kg paper/valve bags

Storage

Keep the product in a dry place and closed in original packing

GENERAL AND RHEOLOGICAL CHARACTERISTICS	
Residue of diameter greater than 75 micron	4% max.
Viscosimeter dial reading at 600 r/min	30 min.
Yield point/Plastic viscosity	3 max.
Filtrate volume	15 max.

Information given in this bulletin is based on the state of our knowledge at the date of publication and are believed to be accurate, but do not constitute any engagement or warranty from our part. Buyers and users should make their own assessments under their own conditions and for their own requirements. Information may be changed without any notice. For mandatory characteristics and performance please refer to our Sale Specifications.