

## BARITE LCM

### TECHNICAL CHARACTERISTICS

Characteristics	
Colour	Pink-brown
moisture	0.2 % max
Bulk density	4.20 min
Wet residue on 200 mesh	3 % max
Wet residue on 325 mesh	5 – 15 %
Fann viscosity (OCMA DFCP-3)	125 cps max
Fann viscosity after addition of CaSO <sub>4</sub>	125 cps max
pH ( OCMA DFCP-3)	10 max
Soluble in water	0.1 % max

Chemical analysis (%)	
BaSO <sub>4</sub>	<b>60 – 70</b>
Fe <sub>2</sub> O <sub>3</sub>	<b>20 - 25</b>
SiO <sub>2</sub>	<b>6 - 10</b>

*Information given in this bulletin is based on the state of our knowledge at the date of publication and are believed to be accurate, but do not constitute any engagement or warranty from our part. Buyers and users should make their own assessments under their own conditions and for their own requirements. Information may be changed without any notice. For mandatory characteristics and performance please refer to our Sale Specifications.*