

LAVIOSA ARGIMEL® S8

Rheological Additive for Solvent Borne Paint and Coatings

General Information

LAVIOSA ARGIMEL® S8 is a rheological additive for all kind of solvent-borne systems, from low to high polarity, that gives excellent thixotropic effect, sag control, levelling and prevents pigments from long-term storage settling.

The nature of **LAVIOSA ARGIMEL® S8** is a bentonite clay, organically modified with a quaternary alkylammonium compound.

Table 1 Chemical-physical properties

| Properties | Description |
|---------------|-------------------------------|
| Composition | organically modified smectite |
| Physical form | white fine powder |
| Bulk density | 0.4-0.6% |
| Moisture | 3% |

Applications

LAVIOSA ARGIMEL® S8 is used in a wide range of paint manufacturing processes, anti-corrosive paints, automotive primers, industrial finishes, anti-fouling paints, printing inks, adhesives and mastics to give the desired rheological control to the system. It provides anti-settling and anti-sagging properties. **LAVIOSA ARGIMEL®**

S8 shows particularly good performance in aromatics, cellosolve, acetates, ketones, glycols, alcohols and resins like epoxies, nitrocellulose, polyacrylates, polyesters, polyurethanes and polyvinyls.

Incorporation

LAVIOSA ARGIMEL® S8 belongs to the conventional type of organoclays group, which requires mechanical energy, shear forces applied with a good dispersion equipment, and a chemical (polar) activator to reach the proper level of delamination of the organo-bentonite platelets. While heat is not essential in most cases, processing temperatures above 20 °C are preferred. Suitable polar activators are low molecular weight species. Propylene carbonate can also be used, even in absence of water.

It is always recommended to determine the proper level of addition with experimental approach because either defect or excess of chemical activator would result in a non-optimal rheology development.



Table 2 Activators' dosage (based on Laviosa ARGIMEL® weight)

| Polar activator | % |
|--------------------------------------|----|
| Acetone/H ₂ O (95:5) | 60 |
| Methanol/H ₂ O (95:5) | 33 |
| Propylene Carbonate | 33 |
| Propylene Carbonate/H ₂ O | 33 |
| Ethanol/H ₂ O | 50 |

Chemical dispersants, able to disperse **LAVIOSA ARGIMEL® S8**, that are available in the market, generally have to be used once organoclay is first dispersed. Several methods can be used to incorporate **LAVIOSA ARGIMEL® S8**:

1. The “*direct add*” technique. **LAVIOSA ARGIMEL® S8** is added directly in powder form to the solvent/resin mix, before pigment addition and milling. It is advisable to allow the organoclay to wet and disperse at first and to add the polar activator before or after the pigments. Surfactants have to be added the last.
2. The “*pregel*” technique. **LAVIOSA ARGIMEL® S8** is added as described above in a suitable solvent at a 5-10% concentration, with a polar activator. The activated gel is then added to the binder

solution and stirred. After pigment addition the mix is finally milled. Higher activated gel concentrations (15-20%) can be obtained with the aid of suitable dispersing additives, always added after full organoclay dispersion.

Dosage

Level of addition strongly depends on the type of system and on the degree of thickening or other properties desired. For house and industrial paints, typical levels are between 0.2% and 0.6% of **LAVIOSA ARGIMEL® S8**. For primers and printing inks, higher levels are required (0.5-1.0%). For strong anti-sagging properties, up to 3.0% can be used. Compared to other products of its type it is also proved to be more versatile in terms of compatibility to a wide range of formulations.

Storage stability and packing

Storage is advisable in a dry, sheltered place in closed bags. **LAVIOSA ARGIMEL® S8** rheological additive is available in 20 kg net paper bags. **LAVIOSA ARGIMEL® S8** has a shelf life of 3 (three) years from date of manufacture.

Rev01 September 2022

Information given in this bulletin is based on the state of our knowledge at the date of publication and are believed to be accurate, but do not constitute any engagement or warranty from our part. Buyers and users should make their own assessments under their own conditions and for their own requirements. Information may be changed without any notice. For mandatory characteristics and performance please refer to our Sale Specifications.

