

Technical Data Sheet

civil engineering@laviosa.com

Construction Technologies Civil Engineering, Drilling & Tunnelling

BENTOSUND 120E 45S[®]

Special formulation based on a selection of additives & natural sodium bentonite specifically designed to be used for a foundation engineering works in every type of soils as

- 1. diaphragm walls,
- 2. Barrettes
- 3. bored piles

It has been engineered to build strong mud viscosity in a fast way, providing a superior hole cleaning thanks to a high gel strength. Moreover, it is recommended in keeping under control lost circulation and formation sloughing, while promoting hole stability in unconsolidated formations. The specific function as a primary filter-cake-building, filtration-control and as suspension agent in freshwater or recycled water is particularly adapted to the different applications even in case of massive seawater and calcium contaminations.

Specific advantages and benefits

- Provides shale control and lubricity with minimal viscosity increase (during contamination)
- Working with any type of drilling equipment
- Hydrates more than other types of Bentonite and is best for developing gels for suspension and controlling filtration
- Small particle size, unique flat shape and high surface area of hydrated

- Provides superior filtration values.
- Promotes the deposition of thin, compressible filter cakes in the bore
- Fast swelling
- Effective across a wide pH range
- Grouting effects
- Good filtration properties
- Low consumption
- Low sensitivity to contaminants (especially soil, salt and cement)
- Stable even at low usage concentrations (up to 30 kg/mc)

Application

BENTOSUND 120E 45S is specifically set-up for special foundation works in all kind of soils. Dosage changes according to the kind of use and to stratigraphy.

Approx. Amounts in freshwater

- normal drilling conditions 35-40 Kg/m3
- unconsolidated Form. 40-45 Kg/m3
- Seawater Contamination 45-50 Kg/m3

Preparation

Mix with water using a high efficient mixer. To get best properties at least 6 hours of aging are required. Keep the mud in circulation during the use.

Packing Storage and Disposal

25 kg paper bags and jumbo bags Keep the product in a dry place and closed in original packing.

Information given in this bulletin is based on the state of our knowledge at the date of publication and are believed to be accurate, but do not constitute any engagement or warranty from our part. Buyers and users should make their own assessments under their own conditions and for their own requirements. Information may be changed without any notice. For mandatory characteristics and performance please refer to our Sale Specifications.

COMPANY WITH QUALITY SYSTEM CERTIFIED BY DNV GL = ISO 9001 =

Laviosa Chimica Mineraria SpA - Italy Laviosa Sanayi ve Ticaret Ltd Sti - Turkey Laviosa MPC sas - France Laviosa Trimex Industries Pvt Ltd - India