

Technical Data Sheet

additives@laviosa.com


Performance Additives **Decorative**

LAVIOKOLL® C4 Construction additive

General information

LAVIOKOLL® C4 is a new additive based on bentonite clay that gives moderate thixotropic properties to system

LAVIOKOLL® C4 prevents the sedimentation of the aggregates and the bleeding of the surface, it also improves the workability of mortars, suitable for mortars.



Composition: smectite (98% montmorillonite)

Physical form : creamy powder

Dry residue : $0\% > 200 \text{ mesh } (75 \mu\text{m})$

Moisture: 11-12%

Application

- mortars
- plaster/renders
- · tile adhesives

Properties

LAVIOKOLL® C4 is a suspending agent that gives antisettling properties and reduces surface bleeding.

The immediate and 24h viscosities can be compared (Fig.1)




Fig.1: Laviokoll C4 - immediate and 24h viscosities

Chemical composition (XRF)

Na2O	0,40
MgO	2,28
Al2O3	14,17
SiO2	72,32
P2O5	0,03
K20	1,87
CaO	0,91
TiO2	0,26
MnO	0,03
Fe2O3	2,33
LOI	5,40

Dosage

Typical dosage is 0.1% e 3% based on the total formulation.

Storage stability and packing

Product do not deteriorate in a significant way in a 12 months period. Storage is advisable in a dry, sheltered place in closed bags. Packing is 25 kg net in paper bags.

Rev 1 July 2012

Information given in this bulletin is based on the state of our knowledge at the date of publication and are believed to be accurate, but do not constitute any engagement or warranty from our part. Buyers and users should make their own assessments under their own conditions and for their own requirements. Information may be changed without any notice. For mandatory characteristics and performance please refer to our Sale Specifications.