

Technical Data Sheet

civil engineering@laviosa.com

Construction Technologies Civil Engineering, Drilling & Tunnelling

BENTOSUND 120E 45 S

BENTOSUND 120E 45S is a natural sodium bentonite which, after a brief dispersion in water and an aging time of about 4/6 hours, shows a rheological reaction that guarantees highly colloidal suspensions which have excellent suspensive and waterproofing characteristics. Its usage recommended for the preparation of support fluids used for special foundations: diaphragm walls, barrettes...

CHEMICAL-PHYSICAL CHARACTERISTICS		MIN	MAX
Total free moisture	%	10	14
Wet residue over 75 micron sieve	%		2
Marsh Viscosity 1500/1000 at 24h (AT 4,5%)		40	
Bleeding at 24h (4,5% suspension)	%	0	
Fluid loss	ml		28
pH of fluid loss		8,5	·
Cake (4,5% suspension)	m m		2

Specific advantages and benefits

- Fast swelling
- Very good filtration properties
- Low consumption
- Low sensitivity to contaminants (soil, salt cement)

Application

BENTOSUND 120E 45 S is specifically set-up for special foundation. It is suitable for all kind of soils

Preparation

Mix with water using a high efficient mixer. To get best properties at least 6 hours of aging are required. Keep mud in circulation during use.

Packaging

Jumbo bags & 25 Kg paper/valve bags

Storage

Keep the product in a dry place and closed in original packing

.

Information given in this bulletin is based on the state of our knowledge at the date of publication and are believed to be accurate, but do not constitute any engagement or warranty from our part. Buyers and users should make their own assessments under their own conditions and for their own requirements. Information may be changed without any notice. For mandatory characteristics and performance please refer to our Sale Specifications.

