

Technical Data Sheet

additives@laviosa.com

Performance Additives

Animal feed

GLOBALFEED AP-I

Selected bentonites as additives in animal feed (1m558i)

Properties and characteristics

GLOBALFEED AP-I is made of an extremely pure bentonite, with very high performances concerning mycotoxines adsorption as shown in the picture.


GLOBALFEED AP-I is a fine powder, not hygroscopic, extremely fluent.

| GLOBALFEED AP-I | | | | | |
|---|----------------------------|----------|--|--|--|
| Physical and Chemical characteristics (typical values): | | | | | |
| Montmorillonite | [%] | min 85 | | | |
| Moisture | [%] | 10 - 14 | | | |
| Cation exchange capacity | [meq/100g] | 90 -110 | | | |
| pH (sospension at 5% in H ₂ O) | | 9,5-10,5 | | | |
| Dry residue on 45 micron | [%] | max 10 | | | |
| Lead content (directive 2005/87/CE) | [ppm] | max 30 | | | |
| Cadmium content (directive 2005/87/CE) | [ppm] | max 2 | | | |
| Dioxines content (directive 2006/13/CE) | [ng WHO PCDD/F-TEQ/kg] | max 0,75 | | | |
| Dioxines content and PCB (directive 2006/13/CE) | [ng WHO PCDD/F-PCB-TEQ/kg] | max 1,5 | | | |
| Chemical analysis (typical): | [%] | | | | |
| Na ₂ O | 2,37 | | | | |
| MgO | 2,47 | | | | |
| Al ₂ O ₃ | 14,38 | | | | |
| SiO ₂ | 50,39 | | | | |
| P ₂ O ₅ | 0,26 | | | | |
| K ₂ O | 0,14 | | | | |
| CaO | 2,05 | | | | |
| TiO ₂ | 1,66 | | | | |
| MnO | 0,03 | | | | |
| Fe ₂ O ₃ | 18,44 | | | | |
| LOI | 7,80 | | | | |





Analysis on the mycotoxins adsorbing capacity



Test conditions:



AFB1 adsorption -

□ *pH* 7- *adsorbent dose* = 0.02%

□ pH 7- adsorbent dose = 0.01%
 □ pH 7- adsorbent dose = 0.001%

Toxin concentration = $1 \mu g/mL$


FB1 adsorption -

pH 7 adsorbent dose 0,1%pH 3 adsorbent dose 0,001%

Toxin concentration = $1 \mu g/mL$








Test conditions:

□ pH 7-Afla B1 concentration= 1 μg/mL
□ pH 7-Afla B1 concentration= 5 μg/mL

Bentonite concentration 0,001%




Test conditions: ■ pH 3-Aflatoxin B1 concentration= 1 μg/mL

Bentonite concentration 0,001%





For **GLOBALFEED AP-I** has also been run an isothermal analysis to find the maximum adsorption capacity.



GLOBALFEED AP-I in the hydrated form has an elevated specific surface, about 800 m²/gr. This characteristic together with colloidal properties provide high adsorption behaviour and Aflatoxin control.





Recommended dose

| RECOMMENDED DOSAGE | | Preventive | Existing contamination |
|--------------------|--------------------|------------|-------------------------------|
| Ruminants | [g/head/day] | 12-50 | 50-100 |
| Others | [Kg / ton of feed] | 0.5-2 | 2-4 |

Packaging

Packaging is 1000 kg big bags, 25 kg paper bags (1250 kg pallet), bulk.

Storage and Shelf Life

Product must be stocked in a dry and clean place.

Shelf life is 5 years from production date.

Rev00 November 2022

Information given in this bulletin is based on the state of our knowledge at the date of publication and are believed to be accurate, but do not constitute any engagement or warranty from our part. Buyers and users should make their own assessments under their own conditions and for their own requirements. Information may be changed without any notice. For mandatory characteristics and performance please refer to our Sale Specifications.

